

ARIHANT PAINT DRIERS

Products	Color	Metal Content %	Non Volatile At 102°C/1Hr %	Specific Gravity At 30° C	Viscosity At 30° C F.C. No 4	Freezing Point		
COBALT OCTOATE	Bluish Violet	12	54	1.034	24	< 2° C		
		6	32	0.87	16	< 2° C		
		3	12	0.83	12	< 0° C		
MANGANESE OCTOATE	Brown	8	50	0.93	70	< 0° C		
		6	37	0.89	25	< 3° C		
LEAD OCTOATE		Pale Yellow	36	75	1.35	27	< 5° C	
	24		45	1.03	13	< 0° C		
	18		33	0.95	12	< 0° C		
CALCIUM OCTOATE	Trace Yellow	10	53	0.99	14	< 5° C		
	Colorless	4	20	0.86	13	< 0° C		
		3	16	0.84	12	< 0° C		
ZINC OCTOATE	Trace Yellow	12	50	0.96	42	< 4° C		
	Colorless	6	27	0.87	15	< 0° C		
ZIRCONIUM OCTOATE		Trace Yellow		18	60	1.10	18	< 0° C
	12		41	0.98	12	< 0° C		
	6		21	0.88	12	< 0° C		
COPPER OCTOATE	Dark Green	8.6	48	0.93	22	< 3° C		
	Green		6	34	0.88	15	< 0° C	
3		16	0.83	13	< 0° C			
IRON OCTOATE	Reddish Brown	3	12	0.82	12	< 0° C		
BARIUM OCTOATE	Yellow	12	51	0.94	20	< 2° C		
CADMIUM OCTOATE								
ANY PRODUCT WILL NOT CONTAIN MORE THAN 0.2% MOISTURE								

ARIHANT COMBINATION DRIERS

	Metal	Color	Non Volatile At 102°C/1Hr	Specific Gravity At 30° C	Viscosity At 30° C F.C. No 4
ADSI 025	Co. 1.5%, Mn 1.5% Pb 17.5%	Purple	52 ± 3	1.05 ± 0.03	18 ± 2
ADSI 028	Co. 2.6%, Mn 2.0% Pb 8.0%	Brown	39 ± 3	0.94 ± 0.03	13 ± 2
ADSI 068	Co. 0.6%, Mn 1.8% Pb 10.8%	Brown	35 ± 3	0.94 ± 0.03	13 ± 2
ADSI 0425	Co. 0.45%, Mn 2.15% Pb 14.0%	Brown	43. ± 3	0.98 ± 0.03	15 ± 2
ADSI 0725	Co. 0.25%, Mn 2.5% Pb 17.5%	Brown	52 ± 3	1.04 ± 0.03	18 ± 2
ADSI 0121	Co. 1.2%, Mn 11.01% ca 2.17%	Blue/Violet	41 ± 3	0.97 ± 0.03	17 ± 2
ADSI 023	Co. 1.00%, Ca 2.0% Zr 2.0%	Blue/Violet	23 ± 3	0.86 ± 0.03	12 ± 2
ADSI 031	Co. 1.66%, Zn 4.66%	Blue/Violet	26 ± 3	0.87 ± 0.03	14 ± 2
ADSI 045	Co. 4.5%, Ba 4.5%	Blue/Violet	37 ± 3	0.90 ± 0.03	14 ± 2